

Microfibrillated Cellulose Products: Environmental and Regulatory Aspects

David Skuse, Ben Bulson, Tom Larson and Daniel Hewson
FiberLean Technologies Ltd



International Conference on Nanotechnology for Renewable Materials

Contents

- Introduction
- Regulatory considerations
- Manufacturing, work place exposure and discharge considerations
- Food contact clearances
- Novel food and food additive allowances
- Environmental Impact
 - Recyclability, Biodegradability and Compostability
 - LCA
- Conclusions



12-16 JUNE 2023 • VANCOUVER, B.C. CANADA

International Conference on Nanotechnology for Renewable Materials


Introduction

- Microfibrillated Cellulose (MFC) – produced by mechanical treatment of cellulose
- Highly viscous suspension in water
- Typically 1-2% solids content
- Satellite production adjacent to final use location
- Produced using stirred media mills




Product families

- MFC from 100% virgin pulp
- MFC from recycled fibres
- MFC mineral composites
- NB Two of these families have no added minerals. MFC only



Coarse MFC




Medium MFC



Fine MFC



Stirred Media Mills



Stirred vessel containing small grinding media beads, which are agitated by an impeller

- Grinding media collide with each other, breaking and fibrillating fibres that are caught in the interstices
- High media surface area enhances fibrillation
- Highly tuneable

Advantages

- No close tolerances or precision engineered components
- Robust proven technology
- Continuous single stage process
- Availability > 95%
- Low Capex and Opex
- High throughput
- Small footprint
- Modular easily-scalable design
- No additives or pre-treatments



Applications

Microfibrillated Cellulose (MFC)

- Increased bonding in fibre-based structures
- Viscosification, highly shear thinning
- Reinforcement (of green polymers)
- Formation of barrier layers

Many applications

- Printing and writing paper
- Packaging
- Paints and coatings
- Adhesives
- Food
- Construction materials
- Nonwovens
- Medical materials



Regulatory considerations

- Moral/ ethical responsibility to produce safe materials and comply with legislation
- Legislative requirements vary around the world
- Typically aspects include:
 - Manufacturing
 - Food contact packaging
 - Food use
 - Environmental impact
- Extensive technical programme around workplace/ environmental exposure, physical chemistry, toxicity, migration behaviour from packaging etc is required
 - Mostly out-sourced from contract laboratories (Fraunhofer etc)
- Don't underestimate the work/ cost
- Start as soon as the product is defined



Initial analysis

- Third party regulatory law firm opinion:
 - Starting materials are either cellulose or cellulose and mineral
 - Starting materials are REACH exempt and have GRAS status
 - Only aspect that needs attention is that the raw materials have been processed and the particle size distribution has got finer
 - Need to consider:
 - Manufacturing - Work place exposure and discharge to the environment
 - Whether chemistry has changed
 - Food contact packaging status
 - Food status



International Conference on Nanotechnology for Renewable Materials

Manufacturing, work place exposure and discharge considerations

Chemistry

- Extensive testing required by various regulatory agencies
- No changes detected compared to feed pulp other than size

| | |
|-----------------------------------|----------------|
| Fibre dimensions (Fiber Analyser) | Shape |
| Particle size (light scattering) | Surface charge |
| SEM Fibril width | Viscosity |
| | pH |
| Molecular mass/ range | Hydrolysis |
| Morphology | Zeta potential |
| Aggregation | |
| Chemical composition | |
| Thermal decomposition profile | |
| Solubility | |

Dusting testing at MFC manufacturing, papermaking and paper shredding locations

- Utilized PM10 nanoparticle detecting technology
- Testing at UK MFC manufacturing facility, US pilot and full scale paper machines and paper shredding simulation
- No nano dust beyond background detected

Discharge

- 10 kg cellulosic residue/tonne MFC
- Either processed through mill effluent system or used for soil remediation





Food contact clearances

- Detailed chemical analysis, comparison with existing GRAS cellulose and migration studies
- Comparison with existing GRAS cellulose
 - Baking paper
 - Tomato ketchup MFC
- Migration studies



Migration Study Results

- Cold (left) and hot (right) water migration sample cumulative count curves
- MFC containing sheets migrated less than control
- Hot migration samples migrated more than their cold migration counterparts
- Show some higher counts in the finer region for MFC containing samples




Migration Study Results

Conclusions

Developed a method for comparative analysis of migrated nano-content using SEM

Fewer counts from sheets made with MFC than from sheets made with standard furnish

- 16-83% less migration from cold water tested samples
- 14-58% less from hot water migration samples
- 29-75% less from dry abrasion tested samples



International Conference on Nanotechnology for Renewable Materials

Regulatory clearances are essential for many applications

Current status

USA

EPA – existing substance under TSCA. Not subject to reporting under EPA nano rule

Food contact clearance through FDA (5wt.% fibrils in packaging), FCNs 1582 and 1887

Covers all ratios of mineral: MFC including mineral-free

Food coating FCN 2022

FDA GRAS – in progress, part of Vireo led consortium. For food use

Canada

Environment and climate change Canada – existing substance under CEPA

Health Canada opinion – “...we see no reason to object...to the use of FiberLean in food contact packaging, under conditions as described on the FDA website in the FCN 1582”

Covers all ratios of mineral: MFC including mineral-free

China

The National Health Commission of the People’s Republic of China approved microfibrillated cellulose pulp (CAS 65996-61-4) as an additive in paper and paperboard used for contact with all types of food, subject to a maximum usage of 5% (based on the dry weight of fiber) and no specific migration level requirement

Covers all ratios of mineral: MFC including mineral-free

Germany

Acceptance confirmed for BfR XXXVI and XXXVI/2 at up to 5 wt.% fibrils when produced with minerals at between 50% and 83% mineral content

Mineral-free application has been filed with BfR

Netherlands

Cellulose microfibrils produced with calcium carbonate, kaolin and/or other permitted mineral fillers are included in Chapter 2 (Paper and board) of the Dutch commodities act regulation at up to 5wt.% fibrils



12-16 JUNE 2023 • VANCOUVER, B.C. CANADA

Novel food and food additive allowances

- Vireo Advisors led consortium working to demonstrate the safety of a range of MFC products in food contact and food applications
- (migration studies) + feeding studies + physical chemistry, toxicological characterisation using *in vitro* gastrointestinal digestion and co culture models

A 90-day dietary study with fibrillated cellulose in Sprague-Dawley rats

Kimberly J Ong¹, James D Ede¹, Cassidy A Pomeroy-Carter¹, Christie M Sayes², Marina R Mullen², Jo Anne Shatkin¹

Affiliations + expand

PMID: 32021807 PMCID: PMC6994281 DOI: 10.1016/j.toxrep.2020.01.003

[Free PMC article](#)

Abstract

Novel forms of fibrillated cellulose offer improved attributes for use in foods. Conventional cellulose and many of its derivatives are already widely used as food additives and are authorized as safe for use in foods in many countries. However, novel forms have not yet been thoroughly investigated using standardized testing methods. This study assesses the 90-day dietary toxicity of fibrillated cellulose, as compared to a conventional cellulose, Solka Floc. Sprague Dawley rats were fed 2 %, 3 %, or 4 % fibrillated cellulose for 90 consecutive days, and parallel Solka Floc groups were used as controls. Survival, clinical observations, body weight, food consumption, ophthalmologic evaluations, hematology, serum chemistry, urinalysis, post-mortem anatomic pathology, and histopathology were monitored and performed. No adverse observations were noted in relation to the administration of fibrillated cellulose. Under the conditions of this study and based on the toxicological endpoints evaluated, the no-observed-adverse-effect level (NOAEL) for fibrillated cellulose was 2194.2 mg/kg/day (males) and 2666.6 mg/kg/day (females), corresponding to the highest dose tested (4 %) for male and female Sprague Dawley rats. These results demonstrate that fibrillated cellulose behaves similarly to conventional cellulose and raises no safety concerns when used as a food ingredient at these concentrations.

Toxicology Research

Issues More Content ▾ Submit ▾ Purchase Alerts About ▾ All Toxicology Research



Volume 9, Issue 3
June 2020

< Previous Next >

Physical, chemical, and toxicological characterization of fibrillated forms of cellulose using an *in vitro* gastrointestinal digestion and co-culture model

Sahar H Pradhan, Marina R Mullen, London R Steele, Matthew Gibb, James D Ede, Kimberly J Ong, Jo Anne Shatkin, Christie M Sayes ✉

Toxicology Research, Volume 9, Issue 3, June 2020, Pages 290–301,
<https://doi.org/10.1093/toxres/tfaa026>

Published: 20 May 2020 [Article history ▾](#)

“ Cite Permissions Share ▾

Abstract


Fibrillated cellulose is a next-generation material in development for a variety of applications, including use in food and food-contact materials. An alternative testing strategy including simulated digestion was developed to



Environmental Impact

- PTS-RH 021:2012 Recyclability testing was carried out by PTS
- Two samples tested: MFC coated paper with bleached and unbleached base sheet

| Sample description | | Sample 1: Bleached | Sample 2: Unbleached |
|-------------------------------|-------------------------|-----------------------------------|-----------------------------------|
| Disintegratability | Non-paper constituents | No information: Not quantified | No information: Not quantified |
| | Total reject | < 1% | < 1% |
| | Recyclable percentage | > 99% | > 99% |
| Sheet formation | Adhesive impurities | Absent | Absent |
| | Optical inhomogeneities | Absent | Absent |
| Overall rating: Recyclability | | Recyclable | Recyclable |



Environmental Impact

- OECD 301B Biodegradability testing was carried out by RespirTek Inc

| Sample description | Biodegradation (%) | Classification |
|--------------------------------------|--------------------|------------------------|
| MFC slurry - no biocide | 75.4 | Ready biodegradability |
| MFC mineral composite - no biocide | 70.4 | Ready biodegradability |
| MFC mineral composite - with biocide | 76.6 | Ready biodegradability |



Environmental Impact

- ISO 20200 (precursor to EN13432) packaging compostability standard testing was carried out by Impact Solutions
- Two samples tested: MFC coated paper with bleached and unbleached base sheet
- Still await compostability data but high level of disintegration is observed.


| Material | R factor | Material recovered from sieving (g) | Degree of disintegration (%) |
|-------------|----------|-------------------------------------|------------------------------|
| White paper | 57.5 | 0.36 | 94 |
| White paper | 57.9 | 0.48 | 92 |
| White paper | 55.8 | 0.05 | 99 |
| Brown paper | 58.1 | 0.11 | 98 |
| Brown paper | 57.0 | 0.79 | 86 |
| Brown paper | 57.1 | 0.14 | 98 |



International Conference on Nanotechnology for Renewable Materials

Environmental Impact

- Life Cycle Analysis (LCA)
 - Cradle to grave LCA for the use of FiberLean MFC in paper applications with different pulp sources and plant locations is in progress with IVL
 - Cradle to gate analysis illustrates the importance of electricity consumption and sourcing
 - Used to focus Process Research work on energy reduction



Conclusions

- Necessary regulatory clearances are in place covering the use of FiberLean MFC in food contact applications at up to 5% by weight MFC in the sheet. Further clearances are in progress.
- Further work to obtain food status for MFC is in progress.
- MFC coated paper is recyclable and biodegradable and is likely compostable.
- MFC slurry is biodegradable.
- MFC LCA is dominated by electricity consumption and sourcing.



International Conference on Nanotechnology for Renewable Materials

Thank you for your attention



We are grateful to TAPPI
for the opportunity to
present this work



FiberLean Technologies Ltd: david.skuse@fiberlean.com



12-16 JUNE 2023 • VANCOUVER, B.C. CANADA